

DATA SHEET

DATE 01.10.11
VERSION 01



DUKKABOARD XL

EXTRA STRENGTH POLYURETHANE ADHESIVE	PRODUCT CHARACTERISTICS
 Three tubes of Dukkaboard XL Extra Strength Polyurethane Adhesive are shown. The tubes are red with white and blue accents. Each tube has a white nozzle with a red tip. The text 'EXTRA STRENGTH POLYURETHANE ADHESIVE' is visible on the tubes.	<p>SOLVENT FREE</p> <p>BINDS DUST</p> <p>SUITABLE FOR HEATED SUBSTRATES</p>
	<p>GENERAL PRODUCT DESCRIPTION</p> <p>Fast setting, waterproof extra strong adhesive.</p> <p>Dukkaboard XL Extra Strength Polyurethane Adhesive is 100% waterproof and will bond to most common building substrates.</p> <p>It can be applied horizontally or vertically to tile backer boards, walls or battens/beams and gives exceptionally high bond strength .</p> <p>The product foams slightly on application to fill any small gaps on uneven surfaces and is resistant to most chemicals.</p>
	<p>PRODUCT USAGE</p> <ul style="list-style-type: none">• Bonds wood, concrete, aluminium and plastic in both interior and exterior applications.• Secures panels in sandwich constructions.• Ideal for bonding window and door frames, staircases and aluminium profiles.

DATA SHEET

DATE 01.10.11

VERSION 01



DUKKABOARD XL

PREPARATION OF SUBSTRATES	HEALTH & SAFETY																													
<p>For optimum curing it is necessary that one of the surfaces is porous. Ensure that the surfaces to be bonded are dry and free from dust, grease and any loose material.</p> <p>Application Apply at room temperature. Gun the adhesive to one of the surfaces to be bonded. Put both surfaces together immediately applying firm pressure without movement. It will set firm within 5 to 10 minutes. Full bond strength is achieved after approximately 24 hours.</p> <p>Finishing Remove any hardened adhesive mechanically. It is the user's responsibility to dispose of all packaging correctly.</p>	<p>Harmful Contains Diphenylmethane diisocyanate. Harmful by inhalation. Irritating to eyes, respiratory system and skin. Limited evidence of a carcinogenic effect. May cause sensitisation by inhalation and skin contact. Harmful: danger of serious damage to health by prolonged exposure through inhalation. Keep out of reach of children. Do not breathe vapour. Wear suitable protective clothing and gloves. In case of accident or you feel unwell, seek medical advice immediately (show the label where possible). If swallowed, seek medical advice immediately and show the container or label. In case of accident by inhalation: remove casualty to fresh air and keep at rest. Contains isocyanates. See information supplied by the manufacturer. Tactile warning applicable. Dispose of empty packaging correctly.</p>																													
TECHNICAL DATA																														
<table><tbody><tr><td>Basis</td><td>PU</td></tr><tr><td>Application temperature</td><td>5°C - 30°C</td></tr><tr><td>Density</td><td>1,12 g/ml</td></tr><tr><td>Solids</td><td>100%</td></tr><tr><td>Open time (23°C/65% RF)</td><td>5 mins</td></tr><tr><td>Hand tight after (23°C/65% RF)</td><td>20 mins</td></tr><tr><td>Final adhesion after (23°C/65% RF)</td><td>24 hours</td></tr><tr><td>Usage</td><td>250-400 g/m²</td></tr><tr><td>Shelf life (stored between 5°C - 25°C)</td><td>12 months</td></tr><tr><td>Temperature resistance after curing</td><td>-30/+80 °C</td></tr><tr><td>Water resistance after curing</td><td>DIN 68602 D4</td></tr><tr><td colspan="2"><i>Mechanical properties 2mm film</i></td></tr><tr><td>Tensile strength (wood to wood 40 kg/cm²)</td><td>10 mins</td></tr><tr><td>Tensile strength (wood to wood 80 kg/cm²)</td><td>30 mins</td></tr><tr><td>Tensile strength (wood to wood 130 kg/cm²)</td><td>24 hours</td></tr></tbody></table>		Basis	PU	Application temperature	5°C - 30°C	Density	1,12 g/ml	Solids	100%	Open time (23°C/65% RF)	5 mins	Hand tight after (23°C/65% RF)	20 mins	Final adhesion after (23°C/65% RF)	24 hours	Usage	250-400 g/m ²	Shelf life (stored between 5°C - 25°C)	12 months	Temperature resistance after curing	-30/+80 °C	Water resistance after curing	DIN 68602 D4	<i>Mechanical properties 2mm film</i>		Tensile strength (wood to wood 40 kg/cm ²)	10 mins	Tensile strength (wood to wood 80 kg/cm ²)	30 mins	Tensile strength (wood to wood 130 kg/cm ²)
Basis	PU																													
Application temperature	5°C - 30°C																													
Density	1,12 g/ml																													
Solids	100%																													
Open time (23°C/65% RF)	5 mins																													
Hand tight after (23°C/65% RF)	20 mins																													
Final adhesion after (23°C/65% RF)	24 hours																													
Usage	250-400 g/m ²																													
Shelf life (stored between 5°C - 25°C)	12 months																													
Temperature resistance after curing	-30/+80 °C																													
Water resistance after curing	DIN 68602 D4																													
<i>Mechanical properties 2mm film</i>																														
Tensile strength (wood to wood 40 kg/cm ²)	10 mins																													
Tensile strength (wood to wood 80 kg/cm ²)	30 mins																													
Tensile strength (wood to wood 130 kg/cm ²)	24 hours																													